



GILSONITE BINDERS

<u>GRADE</u>	<u>SOFTENING POINT</u>		<u>ASH</u>
	<u>°C</u>	<u>°F</u>	
250L	116-127	240-260	0.5%
250P	116-127	240-260	0.5%
ER125	120-125	250-260	<0.5%
300L	139-155	283-310	0.5% Typ., 0.9% Max
300P	139-155	283-310	0.5% Typ., 0.9% Max
LOVIS L	149-160	300-320	0.5%-0.8%
LOVIS P	149-160	300-320	0.5%-0.8%
AF161-L	154-169	310-335	0.5% Typ., 0.9% Max. Guar.
AF161-P	154-169	310-335	0.5% Typ., 0.9% Max. Guar.
325 S.F.	154-169	310-335	0.5% Typ., 0.9% Max. Guar.
AP	159-182	320-360	0.5% Typ., 2.0% Max. Guar.
AR	159-182	320-360	0.5% Typ., 2.0% Max. Guar.
LR	159-182	320-360	0.5% Typ., 2.0% Max. Guar.
APA	165-182	330-360	6.0-10.0 % Typical
LRA	165-182	330-360	6.0-10.0 % Typical
350L	170-180	340-355	0.5% Max. Guaranteed
350P	170-180	340-355	0.5% Max. Guaranteed
CGRADE	171-177	340-350	0.5%
SEALER	184-202	365-395	0.5%
HM-L	185-202	365-395	0.5%
HM-P	185-202	365-395	0.5%
HT-L	>205	>400	<3%
HT-P	>205	>400	<3%
IR200L	207	405	1.05 wt.%
IR200P	207	405	1.05 wt.%

TYPICAL SCREEN SIZES AVAILABLE

4 X 150 MESH

10 X 150 MESH

30 X 250 MESH

65 X 325 MESH



**CUMMINGS-MOORE GRAPHITE CO.**

1646 N. GREEN AVE. DETROIT, MICHIGAN 48209-2093  
 Phone: (313) 841-1615 Fax: (313) 841-4880